

IRONBARK RED

Eucalyptus Sideroxylon



www.brittontimbers.com.au



Description

Heartwood dark red. Sapwood pale yellow.
Texture medium and even. Grain interlocked.

Suitability

- ✓ Boating
- ✓ Cabinet Door
- ✓ Decking & Cladding
- ✓ Flooring & Staircase
- ✓ Furniture
- ✓ Joinery

TECHNICAL INFORMATION

| | | | | | |
|---------------------------------|------|----------------------------|------|---------------------------------|-----------|
| Density (kg/m ³ dry) | 1130 | Hardness (Janka) (kN) | 13 | Resistance to Split in Nailing | Fair |
| Specific Gravity | 1.1 | Finish | Fair | Resistance to Split in Screwing | Fair |
| Modulus of Rupture (MPa dry) | 135 | Stability | Fair | Gluing | Poor |
| Modulus of Elasticity (GPa dry) | 17 | Durable | Yes | Growing Region | NSW & QLD |
| Radial Shrinkage % | 3.5 | Sapwood Lyctid Susceptible | Yes | Availability | Limited |
| Tangential Shrinkage % | 7 | Machining | Fair | | |

New South Wales

116-118 Jemma Rd
Prestons NSW 2170

☎ 02 8783 9900

Victoria

25 Gaine Rd
Dandenong VIC 3175

☎ 03 8769 7111

Queensland

29 Sodium St
Narangba QLD 4504

☎ 07 3888 3351

Tasmania

3 Brittons Rd
Smithton TAS 7330

☎ 03 6452 2522



PEFC/21-31-233



AFS/01-31-233